

TECHNICAL DATA SHEET

Material Specification Criteria | Project Submittal Data



PREMISEAL 280

MEDIUM DENSITY • CLOSED CELL FOAM

PremiSeal 280 is a nominal 2.8 pcf density closed cell polyurethane foam roofing system intended for use by qualified contractors trained in the processing and application of spray polyurethane foam. PremiSeal 280 provides a superior R-value of 6.3 per inch and a continuous insulation without thermal breaks. The PremiSeal roofing system provides excellent self-adhering qualities with superior wind uplift, is self-flashing, seamless and with its closed cell nature provides a durable leak resistant roofing system. Its superior strength provides excellent resistance to foot traffic and abuses. The PremiSeal 280 roofing system can be used in most retrofit or new construction applications.

TYPICAL PHYSICAL PROPERTIES:

| PROPERTY | PREMISEAL 280 | TEST |
|------------------------------------|-------------------------|--------------------|
| R-VALUE | 6.3 / Inch | ASTM C 518 |
| CORE DENSITY | 2.8 LB / Cubic Foot | ASTM D 1622 |
| COMPRESSIVE STRENGTH | 50-60 PSI | ASTM D 1621 |
| TENSILE STRENGTH | 65-75 PSI | ASTM D 1623 Type C |
| CLOSED CELL CONTENT | > 90% | ASTM D 6226 |
| DIMENSIONAL STABILITY | < 4% | ASTM D 2126 |
| WATER ABSORPTION | 0.6% | ASTM C 2842 |
| WIND UPLIFT | 200 lb./ft ² | CSA 123.21 |
| LIQUID COMPONENTS AS SUPPLIED | A (ISO) | B (RESIN) |
| SPECIFIC GRAVITY @ 74°F | 1.24 | 1.19 |
| VISCOSITY (BROOKFIELD) @ 74°F, CPS | 250 | 1000-1200 |
| WEIGHT PER DRUM - LBS | 551 | 500 |

| BUILDING CODE CERTIFICATIONS / FIRE TEST DATA | | |
|---|----------|---------------------------|
| FLAME SPREAD | ASTM E84 | 40 |
| INTERNATIONAL BUILDING CODE (IBC) | Meets | Roofing and Foam Plastics |
| UL LISTING | Listed | TGFU.R26705 |
| FACTORY MUTUAL GLOBAL (FMI) | Meets | FM 4470 |
| CALIFORNIA BUREAU OF HOME FURNISHINGS | Listed | California |
| CALIFORNIA FIRE MARSHAL | Listed | California |
| CANADIAN STANDARDS ASSOCIATION | A123.21 | Wind Uplift |

GENERAL PROPERTIES: PremiSeal 280 is a two-component one to one by volume, spray applied polyurethane foam. The PremiSeal 280 liquid A component (Iso) and B component (Resin) are mixed through specialized proportioning spray equipment to produce a fast curing rigid foam plastic insulation. PremiSeal 280 utilizes an EPA approved, zero ozone depleting blowing agent.

RECOMMENDED USES: PremiSeal 280 is a roofing system designed for use in commercial and industrial applications. Use in lieu of more traditional forms of roofing systems. PremiSeal 280 can be applied as a new system over most decking substrates or over an existing built up roofing system as a cost effective alternative to a complete tear off. PremiSeal 280 is suitable for application to most construction materials including wood, masonry, concrete, metal and most roofing board stock materials. PremiSeal 280 can be applied to clean, dry and sound roofing surfaces such as BUR, mod bit, metal, concrete, single-ply and other properly prepared roofing systems. This system will provide a seamless monolithic roof system with no joints, seams, cracks or mechanical fasteners that would allow moisture, heat or cold to enter. Additional uses of this product are as an exterior coating for industrial tanks, agricultural structures, air barrier system, etc.

PREMISEAL 280

MEDIUM DENSITY • CLOSED CELL FOAM



COMPANION PRODUCTS: To complete the PremiSeal roofing system requires the application of a top coating from our PremiCote line of coatings. The PremiCote line of coatings is designed for specific use with the PremiSeal roof system. PremiCote provides an additional weather-tight seal along with the UV light protection required for exterior spray polyurethane foam applications.

APPLICATION GUIDELINES: Polyurethane foam systems should be processed through commercially available spray equipment designed for that purpose by a qualified professional applicator. All surfaces to be sprayed with PremiSeal 280 should be clean, dry and free of all dirt and contaminants. All metal to which the polyurethane foam is to be applied must be free of oils, grease, etc. Each pass or layer of the polyurethane foam should be at least .5 inch (13 mm) and no more than 1.5 inches (38 mm) thick. Allow at least 10 minutes between each pass to allow for cure and cooling. Multiple layers can be applied to reach the desired thickness and insulation value as well as facilitate positive drainage.

Prior to application of the PremiSeal 280 the substrate should be between 45°-120°F (7°- 49°C). Service temperatures for any surface to be sprayed with polyurethane foam should not exceed 180°-200°F (82°- 93°C). Moisture in the form of rain, fog, frost, dew or high humidity (>85%R.H.) will adversely affect the polyurethane foam formation and physical properties of the finished product. Wind velocities of excess of 15 mph may affect the foam surface texture, cure and physical properties as well as cause possible overspray problems.

The finished surface of the PremiSeal 280 must be protected from the adverse effects of sunlight, which can cause discoloration and degradation. The protective coating or covering should be applied over the polyurethane foam the same day as the application or within 24 hours. A variety of protective coatings designed for use with PremiSeal 280 are available from Premium Spray Products.

Consult the current Premium Spray Products application guidelines for PremiSeal 280 prior to installation. It is the responsibility of the professional applicator to thoroughly understand all equipment technical information and safe operating procedures that pertain to a spray polyurethane foam application.

MATERIAL HANDLING: Due to the reactive nature of these components respiratory protection is mandatory. The vapors and liquid aerosols present during application and for a short period thereafter must be considered – and appropriate protective measures taken – to minimize potential risks from overexposure through inhalation, skin, or eye contact. These protective measures include: adequate ventilation, safety training for installers and other workers, use of appropriate personal protective equipment, and a medical surveillance program. It is imperative that the applicator read and become familiar with all available information on proper use and handling of spray polyurethane foam. Additional Information is available at spraypolyurethane.org, polyurethane.org or by contacting the Premium Spray Products Technical Services dept. of Accella Polyurethane Systems, LLC.

PROPER STORAGE OF RAW MATERIALS: Shelf life is six (6) months from date of manufacture when stored indoors, in the original unopened containers and between the temperatures of 65° to 85°.

TECHNICAL ASSISTANCE: For additional assistance please contact the Premium Spray Products Technical Services dept. of Accella Polyurethane Systems, LLC. at (770) 528-9556.

DISCLAIMER: To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Premium Spray Products to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Premium Spray Products. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY PREMIUM SPRAY PRODUCTS EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



SALES • SERVICE • SOLUTIONS

MCC Equipment & Service Center

2705 East Main Street • Plainfield, Indiana 46168
317-209-1111 • www.mccind.com

MANUFACTURED BY:

ACCELLA POLYURETHANE SYSTEMS, LLC
1255 Kennestone Circle – Ste. 200, Marietta, Ga 30066
(770) 528-9556 • PremiumSpray.com

EMERGENCY NOTIFICATIONS:

CHEMTREC : Material Leaks, Spills or Fire (800) 424-9300

